



ARMORED CONDITION

SLAB-TO-SLAB CONDITION

() - Denotes Millimeters

Nominal Relaxed Dimensions			Movement Range			
Model	"A"	"B"	J.O. Min.	"C"	J.O. Max.	Total Movement
25FW	1"(25)	1 1/4"(32)	11/16"(17)	1/8"(3)	1 5/16"(34)	5/8"(16)
40FW	1-5/8"(41)	2"(51)	1"(25)	1/8"(3)	2"(51)	1"(25)
50FW	2"(51)	2-1/2"(64)	1-3/8"(35)	1/8"(3)	2-5/8"(66)	1-1/4"(32)
65FW	2-1/2"(64)	3 1/4"(82)	1-5/8"(41)	1/8"(3)	3-3/8"(86)	1-3/4"(44)
75FW	3"(76)	3 3/4"(95)	2"(51)	1/8"(3)	4"(102)	2"(51)
100FW	3 7/8"(100)	5"(127)	2-11/16"(68)	1/8"(3)	5-5/16"(135)	2-5/8"(67)
125FW	5"(127)	6 1/8"(155)	3-3/8"(86)	1/8"(3)	6-5/8"(168)	3-1/4"(83)

PROJECT NAME: -

PROJECT LOCATION: -

DRAWING DESCRIPTION:

Wabo®Jeene

DATE: 12/14/06

MODEL: FW

BASF

We create chemistry

Watson Bowman Acme Corp.
95 Pineview Drive Amherst, NY 14228
phone: (716) 691-7566 fax: (716) 691-9239
www.wbacorp.com

Watson
Bowman
Acme

Information provided herein, including but not limited to, any drawing, design, photograph, graphic, or statement(s) ("Materials") are proprietary and the property of Watson Bowman Acme Corporation ("Company"). Reproduction, translation, or reduction to any electronic medium or machine readable form, in whole or part, is strictly prohibited, except for the express purpose for which it has been furnished, without prior written consent of Company. All Materials contained herein are provided by Company for information purposes only. Company reserves the right to amend or withdraw any information contained in the Materials without notice. All technical or other advice by Company, whether verbal or written, concerning products, or the use of products in specific situations ("Advice") is given by Company and is used at the Users own risk.

REVISION NO: -

SHEET NO: 11

DRAWING NO: C-96011